



耐化学性EVA

Chemical resistance EVA(LEVATOP®)

测试周期: 7 天	Testing period: 7 days	温度 Temperature °C	测试等级 Evaluation
丙酮	Acetone	20	UU
氢氧化铵浓缩物	Caustic ammoni (concentrate)	20	U
苯胺	Anilin	100	□
汽油无铅	Benzine unleaded	20	U
汽油ASTM (A)	Benzine ASTM Type A	20	UU
丁醇	Butanol	100	UU
clophenes	Clophene	100	□
柴油	Diesel oil	20	□
联苯	Diphyl	100	□
醋酸50%	Acetic acid 50%	20	U
石油	Crude oil	20	○
天然气	Natural gas	20	UU
航空燃料/煤油	Kerosine	20	U
甘油	Glycerin	100	UU
尿素/尿液	Carbamide	20	UU
取暖油	Fuel oil	20	□
液压油矿物	Hydraulic fluid mineral	20	U
氢氧化钾50%	Potassium hydroxid 50%	20	UU
食盐	Sodium chloride	20	UU
碳氢化合物	Hydrocarbons	20	○/□
羊毛脂	Lanoline	20	○
亚麻籽油	Linseed oil	20	U
甲烷	Methane	20	U
醋酸甲酯(醋)	Methyl acetate (vinegar)	20	U
矿物油ASTM No 1	Mineral oil ASTM No. 1	20	UU
矿物油ASTM No. 3	Mineral oil ASTM No. 3	20	○
碳酸氢钠	Sodium bicarbonate	20	UU
钠	Sodium peroxide	20	U
橄榄油	Olive oil	100	UU
素油	Vegetable oil	100	U
四氯乙烯	Perchlorethylene	20	□
磷酸50%	Phosphoric acid 50%	20	U
吡啶	Pyridine	20	□
丙烷	Propane	20	UU
蓖麻油	Castor oil	20	U
硝酸10%	Nitric acid 10%	20	U
盐酸15%	Hydrochloric acid 15%	20	UU
盐/海/咸水	Salt/Sea/Brine water	20	U/U
硫酸10%	Sulphuric acid 10%	20	U
石油冲击	Shock absorber oil	20	U
松脂	Turpentine oil	20	□
动物脂肪	Adipose	20	○
甲苯	Toluol	20	□
变压器油	Transformer oil	100	U
水	Water	100	UU
过氧化氢30%	Hydrogene peroxide 30%	20	□

U 可使用的/usable

○ 有条件的使用/limited use

□ 不可用/not usable